

Jörlanda 2019-01-09

Chemicals resistance test for Elevate RES and UVELite/UVELite RES

Chemicals resistance tests are done for Elevate RES and UVELite/UVELite RES. 2 layers of each lacquers are applied on bright PVC floor. The tests are performed after 1 week after application. The results are presented below:

	Elevate RES	UVELite RES
Coffee 1h	4,5	5
Water 1h	5	5
Red win 1h	5	5
EtOH 48% 1h	5	5
EtOH 96% 1h	5	4
Yellow mustard 1h	5	5
Oliv oil 1h	5	5
Coffee 16h	4	4
Water 16h	5	5
Red win 16h	5	4,5
EtOH 48% 16h	5	5
EtOH 96% 16h	5	4
Yellow mustard 16h	4	4
Oliv oil 16h	5	5
Ammonia 10% 2min	5	5
Acetone 2min	5	5
Hair color 2min	3	2
Hair bleaches 2min	5	5
Ammonia 10% 10min	5	5
Acetone 10min	5	5
Hair color 10min	2	1
Hair bleaches 10min	5	5
Ammonia 10% 30min	5	5
Acetone 30min	2	5
Hair color 30min	0	0
Hair bleaches 30min	5	5
Ammonia 10% 1h	5	5
Acetone 1h	0	5
Hair color 1h	0	0
Hair bleaches 1h	5	5
BHMR	3 / 5	1 / 4

Jörlanda 2019-01-09

Notes:

0=poor, the floor is destroyed

5=Excellent, no marking

Mona Amiri

Lab manager



Olof Wiksväg 9, SE-444 65 Jörlanda, +46 303 563 30

Direct: +46 303 563 18 | **Mobile:** +46 70 625 63 30

mona.amiri@uvelite.com | www.uvelite.com